

Applicant: DONGGUAN JIAN PLASTIC & METAL PRODUCTS LTD.
NO.3-1, SOUTH GAOBU BLVD
GAOBU, DONGGUAN, CHINA
ZIP CODE: 523278
Attn: LILY/NANCY


Date: Mar 23, 2018

Sample Description:


Several groups of submitted samples said to be
(1A) Two (2) pieces of Yellow velvet material
(2A) Two (2) pieces of Yellow velvet material

| | |
|----------------------------------|----------------------------------|
| Standard | : -- |
| Buyer's Name | : WORLD WIDE |
| Colour | : YELLOW |
| Vendor | : WORLD WIDE |
| Manufacturer | : CHINA |
| Supplier | : CHINA |
| Style No./Name | : -- |
| P.O. No. | : -- |
| Ref. | : YELLOW VELVET AGE RANGE: 3+ |
| Country Of Origin | : MADE IN CHINA |
| Goods Exported To | : WORLD WIDE |
| Date Received/Date Test Started | : Mar 12, 2018 |
| Date Final Information Confirmed | : -- |

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Huang Ning, Andy
Assistant General Manager




Conclusion:


| <u>Index</u> | <u>Test Item</u> | <u>Result</u> |
|--------------|--|---------------|
| 1. | Color Fastness To Washing | No Comment |
| 2. | Total Lead (Pb) Content In Non-Surface Coating Materials | Pass |
| 3. | Total Cadmium (Cd) Content | Pass |

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Huang Ning, Andy
Assistant General Manager



- 1 Color Fastness To Washing (ISO 105 C06 A2S-2010, Single Test, 30 Minutes Mechanical Wash At 40°C In 0.4% ECE Reference Detergent And 0.1% Sodium Perborate Solution With 10 Steel Balls):

(1A)

| | |
|----------------|------------|
| Color Change | Grade 2-3# |
| Color Staining | |
| -Acetate | Grade 4-5 |
| -Cotton | Grade 3 |
| -Nylon | Grade 4-5 |
| -Polyester | Grade 4-5 |
| -Acrylic | Grade 4-5 |
| -Wool | Grade 4-5 |

Remark: # The surface finish was washed off.

Remark: This Test Was Conducted At 3F, Hengyun Building, No.235 Kaifa Avenue, GETDD

- 2 Total Lead (Pb) Content In Non-Surface Coating Materials:

With Reference To CPSC-CH-E1001-08.3:2012/CPSC-CH-E1002-08.3:2012, Acid Digestion Method Was Used And Total Lead Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

| <u>Tested Components</u> | <u>Result In ppm</u> | <u>Applicant's Requirement In ppm</u> |
|--------------------------|----------------------|---------------------------------------|
| (2A) [◇] | ND | 90 |

Remark: ppm = Parts Per Million
Detection limit = 10ppm
ND=Not Detected

Tested Component: Yellow Textile of sample 2A

Remark: [◇] = No Sample Is Submitted For Testing, All Test Results Are Referred To Previous Report GZHT90769550 Dated Feb 09, 2018

3 Total Cadmium (Cd) Content

With reference to EPA 3050B: 1996 and EPA 3051A: 2007, ACID Digestion Method Was Used And Total Cadmium Content Was Determined By Inductively Coupled Argon Plasma Spectrometry.

| <u>Tested Components</u> (2A) [◇] | <u>Result In ppm</u> < 10 | <u>Limit In ppm</u> 75 |
|--|------------------------------|---------------------------|
| Remark: ppm = Parts Per Million Detection Limit = 10ppm | | |

Tested Component: Yellow Textile of sample 2A

Remark: [◇] = No Sample Is Submitted For Testing, All Test Results Are Referred To Previous Report GZHT90769550 Dated Feb 09, 2018

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

GZHT90777996

