

ZHAOSHUN TECHNOLOGY (GUANGDONG) CO., LTD.

PRODUCT INTRODUCTION

ZS-NJ-D959W03

1. Product features

ZS-NJ-D959W03 is one kind of the flame retardant type one-component alcohol silicone sealant which is room temperature curing. This products have the properties such as high strength, good adhesion, good adhesion on alumina, copper, stainless steel and other metal, excellent dielectric and good heat resistance. The general using temperature range is from -60°C~200°C. During the curing process, it will release the alcohols, which with no corrosion to the materials such as polycarbonate(PC) and copper. Absolutely compliance with the EU ROHS's requisition.

2. The typical use

- 1).Adhesive fixing of connectors on the circuit board. Sealed, fixed and shockproof electronic components.
- 2).Adhesive fixing, sealing and anti-hunting of electronic components such as the ignition coil, plug, rectifier tube, the splice of the rectifier tube etc.

3. The technology parameters before the curing and after the curing process

Before the curing	Appearance	white paste
	tack-free time (min)	≤15
	Extrudability (g/s, 25°C)	45~55
	Completely cure time(d)	3~7
After the	Relative density (g/cm ³)	1.55~1.65

Tel: 0769-88416888

Fax: 0769-88891019

Web:rtv-silicone.com

Email: zsilicone@megasun-tech.com

Address:No.1 Dixin Second lane, Dixinwei Road,DongboVillage, Zhongtang Town,Dongguan City,Guangdong Province.

ZHAOSHUN TECHNOLOGY (GUANGDONG) CO., LTD.

PRODUCT INTRODUCTION

curing	Tensile strength (MPa)	≥2.0
	Break elongation (%)	≥70
	Shear strength (MPa)	≥2.0
	Hardness(Shore A)	50~60
	The general use of temperature range (°C)	-60~200
	Volume resistivity (Ω·cm)	≥1×10 ¹⁴
	Dielectric strength (KV/mm)	≥18
	Flame retardant grade	UL94 V-0
	Thermal conductivity[W/(m·K)]	≥0.4

The above performance data are measured at 25 ° C, relative humidity of 55% , cured after 7days, Data caused by the different test conditions or product improvement , The company does not bear any relevant responsibility.

4. Instructions

- 1). Surface cleaning: Cleaning the sticklied and coated surface, remove the rust, dirt and oil.
- 2). Brush the glue: Unscrew the hose cap (or cut open), pushed the glue to clean the surface, evenly distributed so that will be glued surfaces together and fixed.
- 3).Curing: put the glued or sealed parts in the air and let it be natural cured. It's one curing process that cured from the surface to the internal, in less than 24 hours (at room temperature and 55% relative humidity) glue curing depth of 2 ~ 4mm, if the sizing location more deeper, in particular, which is not easily accessible to the air, then the fully curing time will be extended, if the temperature is low, the curing time will be extended too, sealant is fully cured at least 7 days if the thick have 6mm.

Tel: 0769-88416888

Fax: 0769-88891019

Web:rtv-silicone.com

Email: zsilicone@megasun-tech.com

Address:No.1 Dixin Second lane, Dixinwei Road,DongboVillage, Zhongtang Town,Dongguan City,Guangdong Province.

ZHAOSHUN TECHNOLOGY (GUANGDONG) CO., LTD.

PRODUCT INTRODUCTION

5. Note

After Operating, unused glue must be sealed and stored , and tighten the cap immediately,. if the seal has a little crust when use it in the next time, remove it and it will not affect the normal use. During the storage process, the canal orifices may appear a small amount of the curing phenomenon, cleared it and it can use it again, and no affection to the product performance.

6. PACKAGING SPECIFICATIONS

Sample:300mL / tube, 25 tubes / box ; 2.6L / tube, 4 tubes / box.

7. Storage and transportation

- 1, The product must be stored in a cool, dry environment below 25 °C, can be storaged below 25 °C for six months.
- 2, Such products are non-dangerous goods, can be transported as common chemicals. Be careful during transport and prevent the leakage.
- 3, Should be recognized before being used with or without abnormal if the products exceeding retention period.

8.Statement

This article contains a variety of data are for reference only ,and we sure that is reliable. For anyone to adopt the way in which we can't control the result, we will not be responsible for.

Tel: 0769-88416888

Fax: 0769-88891019

Web:rtv-silicone.com

Email: zsilicone@megasun-tech.com

Address:No.1 Dixin Second lane, Dixinwei Road,DongboVillage, Zhongtang Town,Dongguan City,Guangdong Province.